

Will Trend Corp.

Direct Printable Bopp Tape Specification

Product name Item	DTR050(Clear) DWH050(White) DBR050(Tan)
Total Thickness (micron)	50±2
Film Thickness (micron)	28±1
Adhesive Thickness (micron)	22±1
Peel Adhesion (g/inch)	480 ↑
Initial Tack (cm)	4.5 ↓
Tensile Strength (kg/inch)	9 ↑
Elongation (%)	110 ↑
Application of Print	Direct Printable

Test Method:

Peel Adhesive: ASTM-D3330

Initial Tack: PSTC-6

Tensile Strength: ASTM-D3759

Elongation: ASTM-D3759

Remark:

1. Testing condition: Temp.: 23±1℃, R.H.: 50±5%
2. Storage condition: Temp.: 23±2℃, R.H.: 50±5%
3. Shelf life: 12 months.
4. Customers need to test and confirm product for the actual operational

requirement, As with all pressure sensitive materials, this product should be tested thoroughly under end-use conditions to ensure it meets the requirements of the specification application.